



TEST REPORT No. MVZ - 02/15/212

Customer:

**Timber Research and Development
Institute, Prague, s. e.
Notified body No. 1393
Na Florenci 7-9
111 71 Prague 1**

Client:

**KRONOSPAN SRB d.o.o.
17. marta 2
SR - 34 220 Lapovo
Republic of Serbia**

Object of the test:

PARTICLE BOARD

Date: 2015-12-10

Number of pages: 2

Number of annexes: 0

Copies: 2

Copy No. 1: Customer

Copy No. 2: MVZ archive

Copy No: 1

The results of tests contained in this Test Protocol apply only to the subject tested and the Test Protocol does not mean approval of the product by the body granting accreditation or by any other body. The tests outside the extent of accreditation and sub-contracted are designated. The ČIA accreditation does not apply to the results of tests titled „Outside the extent of accreditation“.

The Protocol shall not be copied otherwise but as a whole, and to use its part or section you need the written consent of the testing laboratory.

Original copies have relief stamp.

In case of misunderstanding, the Czech version is valid.



Ing. Anna Součková
Head of Material and product testing department

1. OBJECT AND PURPOSE OF THE TEST:

The purpose of the test is the determination of the formaldehyde release of the supplied sample of particle board.

2. TEST SAMPLES:

Sample codes (laboratory):	sample No. 393/15
Sample name:	particle board
Sample description:	particle board
Producer:	KRONOSPAN SRB d.o.o., 17. marta 2, SR - 34 220 Lapovo, Republic of Serbia
Quantity, size:	3 pieces, (500 x 500) mm
Nominal thickness:	18 mm
Date of production:	unknown
Date of reception:	November 30. 2015
Place of reception:	VVÚD - MVZ
Received:	VVÚD; Šárka Vincíková
Handed down:	NB 1393, Ing. Ludmila Kotenová

3. TEST METHOD:

- ČSN EN 120 Wood based panels - Determination of formaldehyde content - Extract procedure called "Perforator method"
- ČSN EN 322 Wooden boards - Determination of humidity.

4. DATE OF TEST:

2 to 4 December 2015

5. TEST RESULT:

Sample number	393/15
Humidity {%}	5,7
Perforator value (P.V.) {mg HCHO/100 g of a.d. substance}	
Individual	6,6
	6,5
Average	6,5

Prepared by: Alena Rážová

- End of report -